

# Caledonian

## **Aluminium Conductor Cables**


www.caledonian-cables.com n

marketing@caledonian-cables.com

## Aluminum Conductor Steel Reinforced (ACSR) Cables

550 sqmm





#### **APPLICATIONS**

ACSR conductors are widely used for electrical power transmission over long distances, since they are ideal for long overhead lines spans. They are also used as a messenger for supporting overhead electrical cables.

#### **STANDARDS**

DIN 48204

#### CABLE CONSTRUCTION

ACSR conductors are formed by several wires of aluminium and galvanized steel, stranded in concentric layers. The wire or wires which form the core, are made of galvanized steel and the external layer or layers, are of aluminium. Galvanized steel core consist normally of 1, 7 or 19 wires. The diameters of steel and aluminium wires can be the same, or different. By varying the relative proportions of aluminium and steel, the required characteristics for any particular application can be reached. A higher U. T. S. Can be obtained, by increasing steel content, and a higher current carrying capacity by increasing aluminium content.

#### PHYSICAL AND THERMAL PROPERTIES

Ambient Temperature: -5°C - 50°C

Isokeraunic level: 10 - 18 Relative Humidity: 5 - 100%

#### **Electrical Properties**

Density@20°C:

Aluminium: 2.703 kg/dm Galvanised Steel: 7.80 kg/dm Temperature Coefficient@20°C:

Aluminium: 0.00403 (°C) Resistivity@20°C:

Aluminium: Should not exceed 0.028264

Linear Expansivity: Aluminium: 23 x10 (°C)

Galvanised Steel: 11.5 x10 (1/°C)



# Caledonian

## **Aluminium Conductor Cables**

www.caledonian-cables.com

marketing@caledonian-cables.com

## **MECHANICAL PROPERTIES**

Wind Pressure: 80 - 130kg/m² Seismic Acceleration: 0.12 - 0.05g

## **CONSTRUCTION PARAMETERS**

	Nom. Area (AL)	Nom. Area (Steel)	Nom. Area (Total)	Stranding (AL)	Stranding (Steel)	Overall Diameter (Total)	Weight	Breaking Load	Electrical Resistance @20°C	Current Rating
١	mm²	mm²	mm²	no x mm	no x mm	mm	kg/km	kN	Ω/km	А
	550	70	620.9	54/3.6	7/3.6	32.4	2085	167.42	0.0526	737